



Flame Retardant fabric for FR-clothing

# THOR-270

60% MODACRYLIC / 38% COTTON / 2% AS

270 GSM / TWILL 2/1



Fabric name	Thor-270
Fabric weight	270 ± 10 gsm
Composition	60% Modacrylic, 38% Cotton, 2% AS
Full width	152 ± 2 cm
Weave	Twill 2/1
Finishes	FR
Application	FR-clothing
Washing instruction	

## FR & SPECIAL PROPERTIES

Flame retardant	ISO 11612 (A1, A2, B1, C1, E1, F1)	50×60°C ISO 6330
	ISO 11611 (Class 1)	50×60°C ISO 6330
Antistatic	ISO 1149-5	50×60°C ISO 6330
Hi-Vis	EN 20471	50×60°C ISO 6330

## PHYSICAL PROPERTIES

		warp	weft
Tensile strength, N	ISO 13934-1:1999	884	612
Tearing strength, N	ISO 13937-2:2000	21	19
Dimensional Stability To Washing, max	ISO 5077-ISO 15797	<3%	
Abrasion Resistance	ISO 12947-2:1999	N/A	
Pilling Resistance	ISO 12945-2:2001	N/A	

## COLOUR FASTNESS

			Light	Mid	Dark	Special colors
			Orange, Yellow, Red	Green, Grey, Royal Box	Dark Navy, Navy, Royal Blue	Hi-Vis Yellow
Wash Fastness Method E2S (95°C)	ISO 105-C06	Colour Change	n/a	n/a	n/a	4-5
		Stain on Polyester	n/a	n/a	n/a	4-5
Rub Fastness	ISO 105-X12:1995	Wet	n/a	n/a	n/a	4
		Dry	n/a	n/a	n/a	5
Light Fastness	ISO 105-B02		n/a	n/a	n/a	n/a

\* Tested in a non-accredited laboratory. \* N/A - not applicable. [www.xmtextiles.com](http://www.xmtextiles.com)

**XM TEXTILES EUROPE**  
Darius ir Gireno st. 42A, Room 509  
Vilnius, LT-02189, Lithuania  
Tel. +370 52 078 703  
[info@xmtextiles.com](mailto:info@xmtextiles.com)

**XM TEXTILES ROMANIA**  
Sos. Tamasi 20, Hala 6B, Parter,  
Buftea, 070000, Ilfov, Romania  
Tel. +40 31 630 3639  
[info@xmtextiles.com](mailto:info@xmtextiles.com)

**XM TEXTILES ITALIA SRL**  
Viale della Mercanzia 195, Blocco 1A, Centergross  
40050 Funo di Argelato (BO), Bologna, Italy  
Tel. +39 051 952 8202  
[info@xmtextiles.com](mailto:info@xmtextiles.com)