




Fabric name	Neptun-245
Fabric weight	245 ± 5 gsm
Composition	50% Polyester, 50% Cotton
Full width	150 ± 2 cm
Weave	Twill 3/1
Finishes	MR+OR
Area of use	workwear and uniform
Washing instruction	

### Physical properties\*

			warp	weft
1	Tensile strength, N	ISO 13934-1:2013	2082	774
2	Tearing strength, N	ISO 13937-3:2000	35	31
3	Dimensional Stability To Washing, max.	ISO 6330:2000	3.0%	3.0%
4	Abrasion Resistance	ISO 12947-2:2002	30 000	
5	Pilling Resistance (after 1000 rev.)	ISO 12945-2:2000	N/A	
6	Colour Fastness To Washing (cotton+polyester) 60°C, min.	ISO 105-C06:2010		
	Colour change	ISO 105-C06:2010	4-5	
	Colour staining	ISO 105-C06:2010	N/A	
7	Colour Fastness To Perspiration, min.	ISO 105-E04:2013		
	Colour change		4-5	
	Colour staining		4-5	
8	Colour Fastness To Rubbing, min.	ISO 105-X12:2001		
	Dry		4-5	
	Wet		4-5	
9	Colour Fastness To Light	ISO 105-B02:2013	N/A	

\* The values shown are indicative and may vary slightly from batch to batch.

\* N/A - not applicable.

[www.xmtextiles.com](http://www.xmtextiles.com)

#### XM TEXTILES EUROPE

Darius ir Gireno st. 42A, Room 509  
Vilnius, LT-02189, Lithuania  
Tel. +370 52 078 703  
info@xmtextiles.com

#### XM TEXTILES ROMANIA

Sos. Tamasi 20, Hala 6B, Parter,  
Buftea, 070000, Ilfov, Romania  
Tel. +40 31 630 3639  
info@xmtextiles.com

#### XM TEXTILES ITALIA SRL

Viale della Mercanzia 195, Blocco 1A, Centergross  
40050 Funo di Argelato (BO), Bologna, Italy  
Tel. +39 051 952 8202  
info@xmtextiles.com