




Fabric name	Polar Fleece AS-280
Fabric weight	280 ± 5 gsm
Composition	98% polyester, 2% AS
Full width	170 ± 2 cm
Weave	knitted
Finishes	antipilling/brushed
Application	workwear jackets or sport vests
Washing instruction	

Antistatic properties (EN 1149)

1	Antistatic	EN 1149-5 (1149-3 method 2)	5×50°C ISO 6330
---	------------	-----------------------------	-----------------

Physical properties*

			warp	weft
1	Dimensional Stability To Washing, max.	ISO 6330:2000	5.0%	5.0%
2	Abrasion Resistance	ISO 12947-2:2002	> 20 000	
3	Pilling Resistance, as received /after 2000 rubs	ISO 12945-2:2000	4	
4	Colour Fastness To Washing (cotton+polyester) 40°C, min.	ISO 105-C06:2010		
	Colour change	ISO 105-C06:2010	3-4	
5	Colour Fastness To Drycleaning, min.	ISO 105-D01:2010	4-5	
6	Colour Fastness To Rubbing, min.	ISO 105-X12:2001		
	Dry		4	
	Wet		4-5	
7	Colour Fastness To Organic Solvents	ISO 105-X05:1994	4-5	
8	Colour Fastness To Light	ISO 105-B02:2013	> 4	

* The values shown are indicative and may vary slightly from batch to batch.

www.xmtextiles.com

XM TEXTILES EUROPE

Dariaus ir Gireno st. 42A, Room 509
Vilnius, LT-02189, Lithuania
Tel. +370 52 078 703
info@xmtextiles.com

XM TEXTILES ROMANIA

Sos. Tamasi 20, Hala 6B, Parter,
Buftea, 070000, Ilfov, Romania
Tel. +40 31 630 3639
info@xmtextiles.com

XM TEXTILES ITALIA SRL

Viale della Mercanzia 195, Blocco 1A, Centergross
40050 Funo di Argelato (BO), Bologna, Italy
Tel. +39 051 952 8202
info@xmtextiles.com